



FINISS

PRODUCT NO. 1201

PRODUCT USE

QUIKRETE® Finish Coat Stucco is designed for use as a decorative finish over Portland cement base coats or QUIKRETE® One Coat Fiberglass-Reinforced Stucco (#1200). Finish Coat Stucco is manufactured as a complete product requiring only the addition of water. Available in white and gray, Finish Coat Stucco can be colored with QUIKRETE® Stucco & Mortar Color (#1319). The liquid color is premixed with the mixing water prior to the addition of the dry Finish Coat Stucco. Mix thoroughly until uniform in color.

SIZES

- QUIKRETE® Finish Coat Stucco is available in the following sizes:
 - 50 lb (23 kg) bags
 - 80 lb (36 kg) bags
 - 3000 lb (1361 kg) bulk bags

YIELD

- Each 80 lb (36 kg) bag will yield approximately 0.75 ft³ (20 L) of material. Coverage will be approximately 70 ft² (6.5 m²) at 1/8" (3.2 mm). Coverage will vary with texture.

TECHNICAL DATA

ASTM International

- ASTM C109/C109M Standard Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or [50-mm] Cube Specimens)
- ASTM C926 Standard Specification for Application of Portland Cement-Based Plaster

PHYSICAL/CHEMICAL PROPERTIES

QUIKRETE® Finish Coat Stucco is a Portland of Finish Coat Stucco. All surfaces must be clean, structurally sound, and free of any loose or foreign material.

MIXING

WEAR IMPERVIOUS GLOVES, such as nitrile when handling product.

- Blend approximately 2 gal (7.6 L) of water per 80 lb (36.3 kg) bag or 1.25 gal (4.7 L) per 50 lb (22.7 kg) bag
- Place water in the mixer and slowly add the Finish Coat Stucco
- Mix 2 - 3 minutes or until a mortar-like consistency is achieved. Add additional water in small amounts if necessary
- Use QUIKRETE Acrylic Fortifier (#8610) when application is being made to basecoats that have previously dried or when applying to QUIKWALL Surface Bonding Cement (#1230) surfaces
- When QUIKRETE Acrylic Fortifier is required as an internal bonding compound, replace 1/2 gal (1.9 L) of water with 1/2 gal (1.9 L) of Acrylic Fortifier per 80 lb (36 kg) bag or 2.5 pt (1.2 L) per 50 lb (23 kg)

- Install in accordance with ASTM C926 and

